



WIDTH TOLERANCES FOR SOLID SECTIONS (AT SPACE DIMENSIONS)

OVERALL EXTERNAL WIDTH	MIN. THICKNESS OF WEB OR FLANGE	EXTERNAL OR INTERNAL WIDTH TOLERANCES AT TOP OF GAP FOR AN INTERNAL DEPTH									
		Upto & Over	6.5	12.5	19.0	25.0	50.0	75.0	100	125	150
		Less than	6.5	12.5	19.0	25.0	50.0	75.0	100	125	150
Less than 6.5	2.0 and over but less than 2.5	0.28	0.33	0.38	0.43	-	-	-	-	-	-
6.5 and over but less than 12.5	2.0 and over but less than 2.5	0.34	0.39	0.44	0.49	-	-	-	-	-	-
12.5 and over but less than 19.00	2.0 and over but less than 2.5	0.40	0.45	0.50	0.55	-	-	-	-	-	-
19.00 and over but less than 25.00	2.0 and over but less than 2.5	0.46	0.51	0.56	0.61	-	-	-	-	-	-
25 and over but less than 38	2.5 and over but less than 5.0	-	-	-	0.66	0.86	1.07	-	-	-	-
38 and over but less than 50	2.5 and over but less than 5.0	-	-	-	0.76	0.96	1.17	1.37	-	-	-
50 and over but less than 65	2.5 and over but less than 5.0	-	-	-	0.84	1.04	1.24	1.45	1.65	1.85	-
65 and over but less than 75	2.5 and over but less than 5.0	-	-	-	0.94	1.14	1.35	1.55	1.75	1.96	2.16
75 and over but less than 100	5.0 and over but less than 7.5	-	-	-	1.02	1.22	1.42	1.63	1.83	2.03	2.24
100 and over but less than 125	5.0 and over but less than 7.5	-	-	-	1.19	1.40	1.60	1.80	2.01	2.21	2.41
125 and over but less than 150	5.0 and over but less than 7.5	-	-	-	1.35	1.55	1.75	1.96	2.16	2.36	2.56
150 and over but less than 175	less than 7.5	-	-	-	1.52	1.73	1.93	2.13	2.34	2.54	2.74
175 and over but less than 200	less than 7.5	-	-	-	1.68	1.88	2.09	2.29	2.49	2.69	2.90
200 and over but less than 225	less than 7.5	-	-	-	1.85	2.11	2.36	2.62	2.87	3.12	3.38
225 and over but less than 250	7.5 and over	-	-	-	1.80	2.06	2.31	2.56	2.82	3.07	3.33
250 and over but less than 275	7.5 and over	-	-	-	1.96	2.21	2.46	2.72	2.97	3.23	3.48